

# LNP™ STAT-KON™ COMPOUND RX08408

RX08408  
REGION AMERICAS

## DESCRIPTION

LNP STAT-KON RX08408 is a compound based on Nylon 66 containing Carbon Powder. Added features of this material include: Electrically Conductive, High Impact.

## TYPICAL PROPERTY VALUES

Revision 20170913

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, brk, Type I, 5 mm/min	46	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	26	%	ASTM D 638
Tensile Modulus, 50 mm/min	1960	MPa	ASTM D 638
Flexural Modulus, 1.3 mm/min, 50 mm span	1760	MPa	ASTM D 790
Tensile Stress, break, 5 mm/min	47	MPa	ISO 527
Tensile Strain, break, 5 mm/min	26	%	ISO 527
Tensile Modulus, 1 mm/min	1930	MPa	ISO 527
Flexural Stress	61	MPa	ISO 178
Flexural Modulus, 2 mm/min	1850	MPa	ISO 178
<b>IMPACT</b>			
Izod Impact, unnotched, 23°C	1720	J/m	ASTM D 4812
Izod Impact, notched, 23°C	141	J/m	ASTM D 256
Multiaxial Impact	25	J	ISO 6603
Instrumented Impact Total Energy, 23°C	22	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	196	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	12	kJ/m <sup>2</sup>	ISO 180/1A
<b>THERMAL</b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	195	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	60	°C	ASTM D 648
CTE, -30°C to 30°C, flow	1.1E-04	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	1.14E-04	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	165	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	117	°C	ISO 75/Af

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>PHYSICAL</b>			
Moisture Absorption, 50% RH, 24 hrs	0.6	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	3 – 5	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	3 – 5	%	ASTM D 955
Moisture Absorption (23°C / 50% RH)	0.87	%	ISO 62
<b>ELECTRICAL</b>			
Volume Resistivity	1000 – 1000000	Ohm-cm	ASTM D 257
Surface Resistivity	1.E+03 – 1.E+06	Ohm	ASTM D 257
<b>INJECTION MOLDING</b>			
Drying Temperature	80	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	280 – 305	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.